WONDERLITE® PC-175

Polycarbonate CHI MEI CORPORATION



Technical Data

Product Description			
High Flow Polycarbonate			
General			
Material Status	Commercial: Active		
Literature ¹	Technical Datasheet (English)		
UL Yellow Card ²	• E56070-100915709		
Search for UL Yellow Card	CHI MEI CORPORATIONWONDERLITE®		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Features	High Flow		
RoHS Compliance	RoHS Compliant		
Resin ID (ISO 1043)	• >PC<		

Physical	Nominal Value Unit	Test Method
Density (23°C)	1.20 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	65 cm ³ /10min	ISO 1133
Molding Shrinkage	0.50 to 0.70 %	ISO 294-4
Mechanical	Nominal Value Unit	Test Method
Tensile Stress		ISO 527-2/50
Yield	60.0 MPa	
Break	50.0 MPa	
Tensile Strain (Break)	65 %	ISO 527-2/50
Flexural Modulus ⁴	2400 MPa	ISO 178
Flexural Stress ⁴	90.0 MPa	ISO 178
Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength (23°C)	10 kJ/m²	ISO 179
Notched Izod Impact Strength (23°C)	8.0 kJ/m²	ISO 180/1A
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load		ISO 75-2/A
1.8 MPa, Unannealed	124 °C	
1.8 MPa, Annealed	140 °C	
Vicat Softening Temperature		
	140 °C	ISO 306/B50
	145 °C	ISO 306/A50
CLTE - Flow	6.0E-5 to 8.0E-5 cm/cm/°C	ISO 11359-2

Notes

- ¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.
- ² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.
- ³ Typical properties: these are not to be construed as specifications.



Form No. TDS-69703-en

^{4 2.0} mm/min